

Vergelijkingstabel van internationale normen voor roestvast staal

Werkstoff Nr. German	DIN / EN Europe	AISI USA	UNS Unified	SS Swedish	AFNOR French	BS British
1.4005	X12 CrS 13	416	S 41600	2380	Z 11 CF 13	416 S 21
1.4006	X12 Cr 13	410	S 41000	2302	Z 10 C 13	410 S 21
1.4016	X6 Cr 17	430	S 43000	2320	Z 8 C 17	430 S 15
1.4021	X20 Cr 13	420	S 42000	2303	Z 20 C 13	420 S 37
1.4034	X46 Cr 13			2304	Z 40 C 14	(420 S 45)
1.4057	X17 CrNi 16-2	431	S 43100	2321	Z 15 CN 16,02	431 S 29
1.4104	X14 CrMoS 17	430 F	S 43020	2383	Z 13 CF 17	(441 S 29)
1.4112	X90 CrMoV 18	440 B	S 44003			
1.4122	X39 CrMo 17-1					
1.4301	X5 CrNi 18-10	304	S 30400	2332	Z 6 CN 18,09	304 S 15
1.4305	X8 CrNiS 18-9	303	S 30300	2346	Z 8 CNF 18,09	303 S 31
1.4306	X2 CrNi 19-11	304 L	S 30403	2352	Z 2 CN 18,09	304 S 11
1.4310	X10 CrNi 18-8	301	S 30100	2331	Z 12 CN 18,08	301 S 22
1.4401	X5 CrNiMo 17-12-2	316	S 31600	2347	Z 7 CND 17,12,02	316 S 31
1.4404	X2 CrNiMo 17-12-2	316 L	S 31603	2348	Z 3 CND 18,12,02	316 S 11
1.4435	X2 CrNiMo 18-14-3	316 L	S 31603	2353	Z 3 CND 18,14,03	316 S 11
1.4436	X3 CrNiMo 17-13-3	316	S 31600	2343	Z 7 CND 18,12,03	316 S 31
1.4438	X2 CrNiMo 18-15-4	317 L	S 31703	2367	Z 3 CND 19,15,04	317 S 12
1.4439	X2 CrNiMoN 17-13-5	(317 LMN)				
1.4449	X5 CrNiMo 17-13	317	S 31700			317 S 16
1.4460	X3 CrNiMoN 27-5-2	329	S 32900	2324	Z 5 CND 27.05.AZ	
1.4462	X2 CrNiMoN 22-5-3		S 31803	2377	(Z 5 CNDU 21,08)	
1.4539	X1 NiCrMoCu 25-20-5	(904 L)	N 08904	2562	Z 1 NCDU 25,20	
1.4541	X6 CrNiTi 18-10	321	S 32100	2337	Z 6 CNT 18,10	321 S 31
1.4550	X6 CrNiNb 18-10	347	S 34700	2338	Z 6 CNNb 18,10	347 S 31
1.4571	X6 CrNiMoTi 17-12-2	316 Ti	S 31635	2350	Z 6 CNDT 17,12	320 S 31
1.4713	X10 CrAlSi 7				Z 8 CA 7	
1.4724	X 10 CrAl 13				(Z 10 C 13)	
1.4742	X 10 CrAl 18				Z 10 CAS 18	
1.4762	X 10 CrAl 24		(S 44600)		Z 10 CAS 24	
1.4821	X 20 CrNiSi 25 4				Z 20 CNS 25.04	
1.4828	X 15 CrNiSi 20 12	309	(S 30900)		Z 15 CNS 20.12	309 S 24
1.4841	X 15 CrNiSi 25 20	314	S 31400		Z 12 CNS 25.20	314 S 25
1.4845	X 12 CrNi 25 21	310 S	S 31008	2361	Z 12 CN 25.20	310 S 24
1.4864	X 12 NiCrSi 36 16	330	N 08330		Z 12 CNS 35.16	(3076 NA 17)
1.4876	X 10 NiCrAlTi 32 20	B 163			Z 8 NC 32.21	3076 NA 15 H
1.4878	X 12 CrNiTi 18 9	321	S 32100	2337	Z 6 CNT 18.12	321 S 51